

# SCOUGAL RAMP DATA SHEET



- ◆ Bright yellow color for visibility.
- ◆ Durable EPDM material for long lasting savings
- ◆ Through holes every 9” for optional spiking
- ◆ Great ozone / UV resistance
- ◆ Ramps are currently available in 4 foot sections
- ◆ Eliminates the need for cold mix
- ◆ Eliminates the need for disposal of cold mix
- ◆ Installs quickly expediting the plate placement process
- ◆ Highly visible for motorists and pedestrians
- ◆ Eliminates the mess
- ◆ Highly durable and reusable



## PHYSICAL PROPERTIES

ASTM	DESCRIPTION	REQUIREMENT
D2240	- Hardness, Durometer +/- 5Maximum	70
D412	- Tensile Strength, Psi Minimum	1500
D412	- Elongation at Break, % Minimum	300
D573	OVEN AGED - 70 hours @ 212 F	
	- Hardness, Durometer Change Maximum	+15
	- Tensile, % Change Maximum	-15
	- Elongation, % Change Maximum	-40
D395	COMPRESSION SET	
Method B	- 22 hours @ 212 F % Maximum	65
D1149	OZONE 100 pphm in air by volume	
	- 20% strain, 100 +/- 2 F @ 100 hours mounting procedure D518, Proc. A	NO CRACKS
D746	LOW TEMPERATURE IMPACT	
	- Brittle point: -40 F	PASS
D471	WATER ABSORPTION	
	- 70 hours @ 212F volume change % Maximum	3